

NINE E CO., LTD

7F-7, No. 171, Song Teh Road, Taipei, Taiwan, Republic of China.

Tel: 886-2-2759-9188 Fax: 886-2-2759-0333 E-mail: ninee@9e.com.tw

<http://www.9e.com.tw>

LC-101

前言 PREFACE

LC-101 為再濕型接著劑，可用甲醇或乙醇作為溶劑活化 LC-101 接著劑，以供接著之用。
LC-101 is a wet based adhesive. Can use either Methanol or Ethanol as solvent to activate LC-101 adhesive, for the adhesion purpose.

用途 APPLICATION

LC-101 可用於紙，鋁，Polyimide Film (Kapton) 等的接著。有很好的密著性，抗化學性。The LC-101 can be applied as adhesion to paper, aluminum, Polyimide film (Kapton). It has excellent adhesion and chemical resistance.

規格 SPECIFICATION

固型份 Solid : 24%
黏度 Viscosity 25 : 800 ~ 1,500cps
密度 Density, g/cm³ : 0.94
內含溶劑 Solvent : 甲醇 Methanol
稀釋劑 Diluent Solvent : 甲醇 Methanol
清洗劑 Cleaning Solvent : 甲醇 Methanol
乾膜耐溫 Dry Film Heat Resistance : 120

使用 PROCESSING

塗佈量 Coating weight : 視底材而定 Depending on the type of material that is used
乾燥溫度 Drying Temperature : 130 -200 加上足夠風量 plus sufficient blow wind
活化溶劑 Activated Solvent : 甲醇或乙醇 Methanol or Ethanol

安全事項 SAFETY ADVICES

甲醇與甲酚對人體有害。Methanol and cresol are dangerous to your health.

1. 請保持通風的工作環境 Please keep the working environment ventilated.
2. 若不慎與眼睛接觸，請用水沖洗並儘快送醫 If contact to the eyes, please rinse thoroughly with water and consult oculist.
3. 若不慎與皮膚接觸，請立即用水及肥皂沖洗 If contact to the skin, please wash with water and soap immediately.